

March 31, 2006  
Report ID: N0635859

## **REPORT PREPARED FOR:**

Green Glue

## **ANALYTICAL REPORT**

Project: (11) Each Samples Tested in Triplication

Collected by: Green Glue

Date Collected: 02/28/2006

Date Received: 03/01/2006

Analysis: Coating Resistance to Mold Growth (Method: ASTM D-3273-00)

Results @ (28 Days)

Note: 0 = No Resistance; 10 = Complete Resistance

### **SAMPLE RATING: @ 28 DAYS**

| Sample ID:                       | Result | Initial | Units | Final | Units | Weight | Units |
|----------------------------------|--------|---------|-------|-------|-------|--------|-------|
| Jar# 01 of 11 .1% Amical:        | 10     | 193.484 | grams | 208.4 | grams | 14.9   | grams |
| Jar #02 of 11 .2% Amical:        | 10     | 203.678 | grams | 220.9 | grams | 17.2   | grams |
| Jar# 03 of 11 .5% Amical:        | 10     | 196.129 | grams | 213.4 | grams | 17.3   | grams |
| Jar# 04 of 11 1% Amical:         | 10     | 205.1   | grams | 223.3 | grams | 18.2   | grams |
| Jar# 05 of 11 .1% Amical:        | 8      | 207.4   | grams | 222.9 | grams | 15.5   | grams |
| Jar# 06 of 11 .2% Amical:        | 8      | 201.2   | grams | 220.0 | grams | 18.8   | grams |
| Jar# 07 of 11 .5% Amical:        | 8      | 202.6   | grams | 217.3 | grams | 14.7   | grams |
| Jar# 08 of 11 1% Amical:         | 9      | 196.3   | grams | 213.1 | grams | 16.8   | grams |
| Jar# 09 of 11 .2% Amical:        | 8      | 197.9   | grams | 210.3 | grams | 12.4   | grams |
| Jar# 10 of 11 .5% Amical:        | 7      | 205.8   | grams | 217.6 | grams | 11.8   | grams |
| Jar# 11 of 11 Reference Formula: | 10     | 197.8   | grams | 210.7 | grams | 12.9   | grams |

### **COMMENTS:**

Amical is an anti-fungal agent. The "reference formula" is standard Green Glue without Amical.

APPROVED BY:

William W. Ullmann, Ph.D.

President & Technical Director